

Corrosion Test Results of Hexoloy® SA Silicon Carbide



Saint-Gobain Ceramics
Structural Ceramics

Corrosion Test Results in Liquid

Test Environment* Conc. Reagent (Wt%)	Corrosive Weight Loss (mg/cm ² yr)**				
	Temp (°C)	Hexoloy® SA (No Free SiC)	Reaction Bonded SiC (12% SiC)	Tungsten Carbide (6% Co)	Aluminum Oxide (99%)
98% H ₂ SO ₄	100	1.8	55.0	>1000	65.0
50% NaOH	100	2.6	>1000	5.0	75.0
53% HF	25	<0.2	7.9	8.0	20.0
85% H ₃ PO ₄	100	<0.2	8.8	55.0	>1000
70% HNO ₃	100	<0.2	0.5	>1000	7.0
45% KOH	100	<0.2	>1000	3.0	60.0
25% HCl	70	<0.2	0.9	85.0	72.0
10% HF plus 57% HNO ₃	25	<0.2	>1000	>1000	16.0

*Test Time: 125 to 300 hours of submersive testing, continuously stirred.

**Corrosion Weight Loss Guide:

>1000 mg/cm ² yr	Completely destroyed within days.
100 to 99 mg/cm ² yr	Not recommended for service greater than a month.
50 to 99 mg/cm ² yr	Not recommended for service greater than one year.
10 to 40 mg/cm ² yr	Caution recommended based on the specific application.
0.3 to 9.9 mg/cm ² yr	Recommended for long term service.
<0.2 mg/cm ² yr	Recommended for long term service.
	No corrosion, other than as a result of surface cleaning was evidenced.

Saint-Gobain Ceramics
Structural Ceramics
Hexoloy® Products
23 Acheson Drive
Niagara Falls, New York 14303
Telephone: 716-278-6233
Fax: 716-278-2373
E-mail: scd.sales@saint-gobain.com
www.hexoloy.com

©2003 Saint-Gobain Ceramics
All Rights Reserved
Form No. B-1007-1 10/03
Printed in USA

The information recommendations, and opinions set forth herein are offered solely for your consideration, inquiry and verification and are not, in part or total, to be construed as constituting a warranty or representation for which we assume legal responsibility. Nothing contained herein is to be interpreted as authorization to practice a patented invention without a license.
Hexoloy® is a trademark of Saint-Gobain Ceramics.